



Technical Information

Product name	:	MoTip Deco Effect Metallic Lacquer				
Colour	:	Brilliant Silver	Aluminium	Sparkling Silver	Silver	
Article number	:	302501	302502	302503	302504	
Colour	:	Gold	Brilliant Gold	Real Gold	Antique Gold	
Article number	:	302505	302506	302507	302508	
Colour	:	Blue	Black	Red	Violet	Green
Article number	:	302509	302510	302511	302512	302513

Supplier / Producer : MOTIP DUPLI B.V.
Wolframweg 2
NL-8471 XC WOLVEGA
Telephone number +31 561 – 69 44 00
Telefax number +31 561 – 69 44 31

Product description

High quality decorative lacquer to treat surfaces, treated and untreated, of wood, metal, aluminium, glass, stone and various types of plastic.

Product characteristics

Fast drying
Rub resistant
Non-fading and UV resistant
Resistant to weather influences
Scratch free and wear-resistant
Excellent adhesion

Physical and Chemical Characteristics

Contents : 400 ml
Base : Nitro-cellulose binder
VOC-content : Approximately 93% w/w
Solid content : Approximately 7% w/w
Coverage : 1,25 to 1,75 m²
Dust dry : After 5 to 10 minutes
Tack free : After 10 to 20 minutes
Hardened/re-sprayable : After 2 hours
Heat resistant : To 110°C

Usage

Before use, carefully read the directions on the packaging and act accordingly.

Pre Treatment

The surface should be clean, dry and free of grease. Remove loose old lacquer and rust, sand the surface and apply a layer of MoTip Deco Effect **white** primer. When treating surfaces of plastic, first apply a layer of MoTip Deco Effect plastic primer before applying the MoTip Deco Effect white primer. After drying, sand the base layer (grain 600).

Treatment

The surface should be clean, dry and free of grease. The aerosol should have room temperature. Best processing temperature 15 to 25°C. Before use, shake the aerosol for 2 minutes and spray a sample. Distance to the surface to be treated approximately 25 to 30 centimetre.

Apply the lacquer in several thin layers. Before applying the next layer, again shake the aerosol.

After use, clean the valve (turn aerosol upside down and press the nozzle for approximately 5 seconds).

The drying time depends on the ambient temperature, the humidity of the air and the thickness of the lacquer applied.